



m/s Victoria Carpets Co Pty Ltd
7-29 Gladstone Rd, Dandenong Vic 3175
Attn: Mr Matt Ilott

TEST REPORT No. 125900
LABORATORY REF: P125900

CUSTOMER REFERENCE

TUTOR TWIST SUPREME

Sample description as provided by customer
Mass/unit area 40 oz/yd²
Construction Details **Tufted** Secondary Backing **Jute**
Style **Twist Pile**

Order No. 40487
Pile Fibre Content **80% WOOL & 20% SYNTHETIC**
Colour **Fawn**
Pile Height **9.0 mm**

TEST METHOD AS/ISO 9239.1 2003 Reaction To Fire Tests For Floorings Part 1 Determination of the Burning Behaviour Using a Radiant Heat Source. As required by specification C1.10a of the Building Code of Australia.

The test values relate to the behaviour of the test specimens of a product under the particular conditions of the test, they are not intended to be the sole criterion for assessing the potential fire hazard of the product. Clause 9 of AS/ISO 9239 Part 1.

Conditioning as specified in BS EN 13238.2001

Sample submitted Date **Oct 2012**

Test Date **27 Nov 2012**

ASSEMBLY SYSTEM: OVER UNDERLAY AIRSTEP STEPEZY

The UNDERLAY used was **AIRSTEP STEPEZY**.

Substrate: Non-Combustible

Substrate - 6mm Fibre Reinforced Cement Board to simulate a Non-Combustible Flooring.

The Holding Torque on Specimen Frame was 2Nm.

Initial Test Specimen 1 Length Direction Critical Radiant Flux **2.8 kW/m²**
Specimen 1 Width Direction Critical Radiant Flux **2.7 kW/m²**
Full tests carried out in the **Width** Direction

SPECIMEN	Width #1	Width #2	Width #3	Mean
Critical Radiant Flux (kW/m ²)	2.7	2.8	2.9	2.7
Smoke Development Rate (%.min)	222	251	236	236

The values quoted below are as required by Specification C1.10a Fire Hazard Properties (Floors) of the Building Code of Australia. The Critical Radiant Flux quoted is the value at Flame-Out/Extinguishment (BCA General Provisions A1.1).

MEAN CRITICAL RADIANT FLUX 2.7 kW/m²

MEAN SMOKE DEVELOPMENT RATE 236 percent-minutes

OBSERVATIONS: The samples singed ,ignited and burnt a relatively short distance



M. B. Webb
Technical Manager
DATE: 27 Nov 2012

Measurement Science & Technology No. 15393
Accredited for compliance with ISO/IEC 17025.



PAGE 1 of 2

This Page (1) has been designed to show the values required under Specification C1.10a Fire Hazard Properties (Floors) of the Building Code of Australia.

The values on Page 2 have no relevance to the Code.

1004 04 09

APL Australia Pty Ltd
5 Carinish Rd, Oakleigh South
Victoria 3167 Australia

Telephone: 03 9543 1618
Facsimile: 03 9562 1818
Mobile: 0411 039 088

Email: apl@aplaustralia.com.au
Web: www.aplaustralia.com.au
ABN 69 468 849 319