

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106


1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : Hotel Carpet
2099 Princes Hwy
Clayton VIC 3168

Test Number : 24-000247
Issue Date : 14/02/2024
Print Date : 4/03/2024

Sample Description Clients Ref : "Axminster 7x8"
Cut pile carpet
Colour : Black/Grey/Blue
End Use : Flooring
Nominal Composition : 80% Wool, 20% Nylon
Nominal Mass per Unit Area/Density : 1287g/m²
Nominal Thickness : 7mm



316665

68861

Page 1 of 2

© Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing
Accreditation Numbers: 963, 985, and 1355

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.



Fiona McDonald
APPROVED SIGNATORY

MICHAEL A. JACKSON B.Sc (Hons)
MANAGING DIRECTOR

AWTA PRODUCT TESTING

Australian Wool Testing Authority Ltd - trading as AWTA Product Testing
A.B.N 43 006 014 106

1st Floor, 191 Racecourse Road, Flemington, Victoria 3031
P.O Box 240, North Melbourne, Victoria 3051
Phone (03) 9371 2400

TEST REPORT

Client : Hotel Carpet
2099 Princes Hwy
Clayton VIC 3168

Test Number : 24-000247
Issue Date : 14/02/2024
Print Date : 4/03/2024

AS 4586-2013
Appendix A

Slip Resistance Classification of New Pedestrian Surface Materials Dry Pendulum Test Method

Date of Testing 14-02-2024
Operator AWTA Test Operator 4
Test Temperature 23 °C
Sample tested as received

Pile Direction	Length
Fixed/Unfixed	Unfixed
Slider No 96 Batch No	23
Length	1 2 3 4 5 SRV
British Pendulum Number	70 72 71 70 70 71

Classification (Surface tested dry) P5

Equipment: Cooper Pendulum Skid Tester Serial No: 1433-01 Calibrated 11/10/2023
Slider prepared using P400 and 3µm lapping film.

These results apply only to the specimens tested and it is recommended that before selection of flooring or paving materials the effect of service conditions, including maintenance and wear on their slip resistance be checked.

316665

68861

Page 2 of 2

Australian Wool Testing Authority Ltd
Copyright - All Rights Reserved



Accredited for compliance with ISO/IEC 17025 - Testing
Accreditation Numbers: 983, 985, and 1356

Samples and their identifying descriptions have been provided by the client unless otherwise stated. AWTA Ltd makes no warranty, implied or otherwise, as to the source of the tested samples. The above test results relate only to the sample or samples tested. This document shall not be reproduced except in full and shall be rendered void if amended or altered. This document, the names AWTA Product Testing and AWTA Ltd may be used in advertising providing the content and format of the advertisement have been approved by the Managing Director of AWTA Ltd.

Fiona McDonald
APPROVED SIGNATORY



MICHAEL A. JACKSON B.Sc.(Hons)
MANAGING DIRECTOR